

GOVERNMENT OF GOA
SD III (QC) , WRD, GOGAL, MARGAO- GOA.

NAME OF THE WORK: Providing flood control measures to the nallah at Deulwada in Village Betoda of Shiroda Constituency.

SAMPLE SENT BY: AE, SD IV, WD XI, WRD, Ponda- Goa.

NAME OF THE AGENCY

TESTING PERIOD

28 days.

REPORT NO	SAMPLE NOS.	CASTING DATE	TESTING DATE	LOCATION OF SAMPLE	MIX PROPOTION	TARGET STRENGTH	Comp sth in Kg/cm2	Avg. Comp Kg/cm2	LETTER No / DATED
1.1	F.68/11/2023						231.11		No. WRD/WD XI/ SD IV/ W.F 566/ 705(A) /2023-24. DATED: 07-03-2024.
	F.68/12/2023	18-02-2024	18-03-2024	For Foundation	1.2.4	210 kg/cm2	222.22	225.18	
	F.68/13/2023						222.22		
1.2	F.68/14/2023						231.11		do
	F.68/15/2023	18-02-2024	18-03-2024	For Foundation	1.2.4	210 kg/cm2	231.11	228.15	
	F.68/16/2023						222.22		
1.3	F.68/17/2023						226.67		do
	F.68/18/2023	18-02-2024	18-03-2024	For Foundation	1.2.4	210 kg/cm2	235.56	231.11	
	F.68/19/2023						231.11		
1.4	F.68/20/2023						235.56		do
	F.68/21/2023	18-02-2024	18-03-2024	For Foundation	1.2.4	210 kg/cm2	213.33	228.15	
	F.68/22/2023						235.56		
2.1	F.68/23/2023						226.67		do
	F.68/24/2023	19-02-2024	18-03-2024	For Foundation	1.2.4	210 kg/cm2	235.56	225.19	
	F.68/25/2023						213.33		
2.2	F.68/26/2023						231.11		do
	F.68/27/2023	19-02-2024	18-03-2024	For Foundation	1.2.4	210 kg/cm2	226.67	228.15	
	F.68/28/2023						226.67		
2.3	F.68/29/2023						226.67		do
	F.68/30/2023	19-02-2024	18-03-2024	For Foundation	1.2.4	210 kg/cm2	231.11	229.63	
	F.68/31/2023						231.11		
2.4	F.68/32/2023						231.11		do
	F.68/33/2023	19-02-2024	18-03-2024	For Foundation	1.2.4	210 kg/cm2	217.78	228.15	
	F.68/34/2023						235.56		

JUNIOR ENGINEER.

ASSISTANT ENGINEER

GOVERNMENT OF GOA
SD III (QC) , WRD, GOGAL, MARGAO- GOA.

NAME OF THE WORK: Providing flood control measures to the nallah at Deulwada in Village Betoda of Shiroda Constituency.

SAMPLE SENT BY: AE, SD IV, WD XI, WRD, Ponda- Goa.

NAME OF THE AGENCY

TESTING PERIOD

28 days.

REPORT NO	SAMPLE NOS.	CASTING DATE	TESTING DATE	LOCATION OF SAMPLE	MIX PROPOTION	TARGET STRENGTH	Comp sth in Kg/cm2	Avg. Comp Kg/cm2	LETTER No / DATED
3.1	F.68/35/2023						226.67		No. WRD/WD XI/ SD IV/ W.F 566/ 705(A) /2023-24. DATED: 07-03-2024.
	F.68/36/2023	20-02-2024	19-03-2024	For Foundation	1.2.4	210 kg/cm2	231.11	226.67	
	F.68/37/2023						222.22		
3.2	F.68/38/2023						235.56		do
	F.68/39/2023	20-02-2024	19-03-2024	For Foundation	1.2.4	210 kg/cm2	222.22	226.67	
	F.68/40/2023						222.22		
3.3	F.68/41/2023						231.11		do
	F.68/42/2023	20-02-2024	19-03-2024	For Foundation	1.2.4	210 kg/cm2	231.11	225.18	
	F.68/43/2023						213.33		
3.4	F.68/44/2023						235.56		do
	F.68/45/2023	20-02-2024	19-03-2024	For Foundation	1.2.4	210 kg/cm2	222.22	228.15	
	F.68/46/2023						226.67		
3.5	F.68/47/2023						231.11		do
	F.68/48/2023	20-02-2024	19-03-2024	For Foundation	1.2.4	210 kg/cm2	231.11	229.63	
	F.68/49/2023						226.67		
3.6	F.68/50/2023						231.11		do
	F.68/51/2023	20-02-2024	19-03-2024	For Foundation	1.2.4	210 kg/cm2	231.11	226.67	
	F.68/52/2023						217.78		

JUNIOR ENGINEER.

ASSISTANT ENGINEER

GOVERNMENT OF GOA
SD III (QC) , WRD, GOGAL, MARGAO- GOA.

NAME OF THE WORK: Providing flood control measures to the nallah at Deulwada in Village Betoda of Shiroda Constituency.

SAMPLE SENT BY: AE, SD IV, WD XI, WRD, Ponda- Goa.

NAME OF THE AGENCY

TESTING PERIOD

28 days.

REPORT NO	SAMPLE NOS.	CASTING DATE	TESTING DATE	LOCATION OF SAMPLE	MIX PROPORTION	TARGET STRENGTH	Comp sth in Kg/cm2	Avg. Comp Kg/cm2	LETTER No / DATED
4.1	F.68/53/2023						235.56		No. WRD/WD XI/ SD IV/
	F.68/54/2023	28-02-2024	27-03-2024	For Middle band	1.2.4	210 kg/cm2	231.11	226.67	W.F 566/ 705(A) /2023-24.
	F.68/55/2023						213.33		DATED: 07-03-2024.
4.2	F.68/56/2023						231.11		
	F.68/57/2023	28-02-2024	27-03-2024	For Middle band	1.2.4	210 kg/cm2	226.67	228.15	do
	F.68/58/2023						226.67		
5.1	F.68/59/2023						235.56		
	F.68/60/2023	6/3/2024	3/4/2024	For Top band	1.2.4	210 kg/cm2	231.11	228.15	do
	F.68/61/2023						217.78		
5.2	F.68/62/2023						235.56		
	F.68/63/2023	6/3/2024	3/4/2024	For Top band	1.2.4	210 kg/cm2	217.78	226.67	do
	F.68/64/2023						226.67		

JUNIOR ENGINEER.

ASSISTANT ENGINEER