

GOVERNMENT OF GOA
SD III (QC) , WRD, GOGAL, MARGAO- GOA.

NAME OF THE WORK: Improvement and Strengthening of bunds at Corjem fields from Sy.No. 108/2 to from 101/1 to Sy. 101/19 in Curtorim Constituency.

SAMPLE SENT BY: AE, SD III, WD II, WRD, Fatorda- Goa.

NAME OF THE AGENCY

TESTING PERIOD

28 days.

REPORT NO	SAMPLE NOS.	CASTING DATE	TESTING DATE	LOCATION OF SAMPLE	MIX PROPOTION	TARGET STRENGTH	Comp sth in Kg/cm2	Avg. Comp Kg/cm2	LETTER No / DATED
1.1	F.98/05/2023						226.67		No. WRD/ SD III/ WD II/ F.17/Camp/2024-25. DATED: 27-05-2024
	F.98/06/2023	3/5/2024	31-05-2024		1.2.4	210 kg/cm2	231.11	229.63	
	F.98/07/2023						231.11		
1.2	F.98/08/2023						235.56		do
	F.98/09/2023	3/5/2024	31-05-2024		1.2.4	210 kg/cm2	222.22	229.63	
	F.98/10/2023						231.11		
2.1	F.98/11/2023						231.11		do
	F.98/12/2023	4/5/2024	1/6/2024		1.2.4	210 kg/cm2	235.56	228.15	
	F.98/13/2023						217.78		
2.2	F.98/14/2023						231.11		do
	F.98/15/2023	4/5/2024	1/6/2024		1.2.4	210 kg/cm2	226.67	226.67	
	F.98/16/2023						222.22		
3.1	F.98/17/2023						231.11		do
	F.98/18/2023	6/5/2024	3/6/2024		1.2.4	210 kg/cm2	226.67	228.15	
	F.98/19/2023						226.67		
3.2	F.98/20/2023						231.11		do
	F.98/21/2023	6/5/2024	3/6/2024		1.2.4	210 kg/cm2	226.67	229.63	
	F.98/22/2023						231.11		
4.1	F.98/23/2023						231.11		do
	F.98/24/2023	8/5/2024	5/6/2024		1.2.4	210 kg/cm2	235.56	231.11	
	F.98/25/2023						226.67		
4.2	F.98/26/2023						222.22		do
	F.98/27/2023	8/5/2024	5/6/2024		1.2.4	210 kg/cm2	231.11	229.63	
	F.98/28/2023						235.56		

JUNIOR ENGINEER.

ASSISTANT ENGINEER

GOVERNMENT OF GOA

SD III (QC) , WRD, GOGAL, MARGAO- GOA.

NAME OF THE WORK: Improvement and Strengthening of bunds at Corjem fields from Sy.No. 108/2 to from 101/1 to Sy. 101/19 in Curtorim Constituency.

SAMPLE SENT BY: AE, SD III, WD II, WRD, Fatorda- Goa.

NAME OF THE AGENCY

TESTING PERIOD

28 days.

REPORT NO	SAMPLE NOS.	CASTING DATE	TESTING DATE	LOCATION OF SAMPLE	MIX PROPOTION	TARGET STRENGTH	Comp sth in Kg/cm2	Avg. Comp Kg/cm2	LETTER No / DATED
5.1	F.98/29/2023						235.56		No. WRD/ SD III/ WD II/
	F.98/30/2023	9/5/2024	6/6/2024		1.2.4	210 kg/cm2	226.67	231.11	F.17/Camp/2024-25.
	F.98/31/2023						231.11		DATED: 27-05-2024
5.2	F.98/32/2023						222.22		
	F.98/33/2023	9/5/2024	6/6/2024		1.2.4	210 kg/cm2	231.11	225.18	do
	F.98/34/2023						222.22		
6.1	F.98/35/2023						235.56		
	F.98/36/2023	11/5/2024	8/6/2024		1.2.4	210 kg/cm2	231.11	228.15	do
	F.98/37/2023						217.78		
6.2	F.98/38/2023						222.22		
	F.98/39/2023	11/5/2024	8/6/2024		1.2.4	210 kg/cm2	235.56	228.15	do
	F.98/40/2023						226.67		
7.1	F.98/41/2023						231.11		
	F.98/42/2023	11/5/2024	8/6/2024		1.2.4	210 kg/cm2	226.67	231.11	do
	F.98/43/2023						235.56		
7.2	F.98/44/2023						231.11		
	F.98/45/2023	11/5/2024	8/6/2024		1.2.4	210 kg/cm2	226.67	229.63	do
	F.98/46/2023						231.11		
8.1	F.98/47/2023						231.11		
	F.98/49/2023	13-05-2024	10/6/2024		1.2.4	210 kg/cm2	226.67	228.15	do
	F.98/50/2023						226.67		
8.2	F.98/51/2023						235.56		
	F.98/52/2023	13-05-2024	10/6/2024		1.2.4	210 kg/cm2	226.67	229.63	do
	F.98/53/2023						226.67		

JUNIOR ENGINEER.

ASSISTANT ENGINEER

GOVERNMENT OF GOA

SD III (QC) , WRD, GOGAL, MARGAO- GOA.

NAME OF THE WORK: Improvement and Strengthening of bunds at Corjem fields from Sy.No. 108/2 to from 101/1 to Sy. 101/19 in Curtorim Constituency.

SAMPLE SENT BY: AE, SD III, WD II, WRD, Fatorda- Goa.

NAME OF THE AGENCY				TESTING PERIOD		28 days.			
REPORT NO	SAMPLE NOS.	CASTING DATE	TESTING DATE	LOCATION OF SAMPLE	MIX PROPOTION	TARGET STRENGTH	Comp sth in Kg/cm2	Avg. Comp Kg/cm2	LETTER No / DATED
9.1	F.98/54/2023						226.67		No. WRD/ SD III/ WD II/ F.17/Camp/2024-25. DATED: 27-05-2024
	F.98/55/2023	13-05-2024	10/6/2024		1.2.4	210 kg/cm2	226.67	229.63	
	F.98/56/2023						235.56		
9.2	F.98/57/2023						231.11		
	F.98/58/2023	13-05-2024	10/6/2024		1.2.4	210 kg/cm2	222.22	228.15	do
	F.98/59/2023						231.11		
10.1	F.98/60/2023						226.67		
	F.98/61/2023	14-05-2024	11/6/2024		1.2.4	210 kg/cm2	240.00	228.15	do
	F.98/62/2023						217.78		
10.2	F.98/63/2023						231.11		
	F.98/64/2023	14-05-2024	11/6/2024		1.2.4	210 kg/cm2	231.11	229.63	do
	F.98/65/2023						226.67		
11.1	F.98/66/2023						231.11		
	F.98/67/2023	16-05-2024	13-06-2024		1.2.4	210 kg/cm2	231.11	229.63	do
	F.98/68/2023						226.67		
11.2	F.98/69/2023						235.56		
	F.98/70/2023	16-05-2024	13-06-2024		1.2.4	210 kg/cm2	240.00	228.15	do
	F.98/71/2023						208.89		
12.1	F.98/72/2023						235.56		
	F.98/73/2023	18-05-2024	15-06-2024		1.2.4	210 kg/cm2	231.11	231.11	do
	F.98/74/2023						226.67		
12.2	F.98/75/2023						222.22		
	F.98/76/2023	18-05-2024	15-06-2024		1.2.4	210 kg/cm2	235.56	229.63	do
	F.98/77/2023						231.11		

JUNIOR ENGINEER.

ASSISTANT ENGINEER

GOVERNMENT OF GOA

SD III (QC) , WRD, GOGAL, MARGAO- GOA.

NAME OF THE WORK: Improvement and Strengthening of bunds at Corjem fields from Sy.No. 108/2 to from 101/1 to Sy. 101/19 in Curtorim Constituency.

SAMPLE SENT BY: AE, SD III, WD II, WRD, Fatorda- Goa.

NAME OF THE AGENCY				TESTING PERIOD		28 days.			
REPORT NO	SAMPLE NOS.	CASTING DATE	TESTING DATE	LOCATION OF SAMPLE	MIX PROPOTION	TARGET STRENGTH	Comp sth in Kg/cm2	Avg. Comp Kg/cm2	LETTER No / DATED
13.1	F.98/78/2023						231.11		No. WRD/ SD III/ WD II/
	F.98/79/2023	20-05-2024	17-06-2024		1.2.4	210 kg/cm2	226.67	228.15	F.17/Camp/2024-25.
	F.98/80/2023						226.67		DATED: 27-05-2024
13.2	F.98/81/2023						235.56		
	F.98/82/2023	20-05-2024	17-06-2024		1.2.4	210 kg/cm2	222.22	229.63	do
	F.98/83/2023						231.11		
14.1	F.98/84/2023						226.67		
	F.98/85/2023	22-05-2024	19-06-2024		1.2.4	210 kg/cm2	226.67	225.19	do
	F.98/86/2023						222.22		
14.2	F.98/87/2023						235.56		
	F.98/88/2023	22-05-2024	19-06-2024		1.2.4	210 kg/cm2	213.33	226.67	do
	F.98/89/2023						231.11		
14.3	F.98/90/2023						235.56		
	F.98/91/2023	22-05-2024	19-06-2024		1.2.4	210 kg/cm2	222.22	228.15	do
	F.98/92/2023						226.67		
15.1	F.98/93/2023						231.11		
	F.98/94/2023	24-05-2024	21-06-2024		1.2.4	210 kg/cm2	222.22	226.67	do
	F.98/95/2023						226.67		
15.2	F.98/96/2023						226.67		
	F.98/97/2023	24-05-2024	21-06-2024		1.2.4	210 kg/cm2	226.67	225.19	do
	F.98/98/2023						222.22		
16.1	F.98/99/2023						222.22		
	F.98/100/2023	25-05-2024	22-06-2024		1.2.4	210 kg/cm2	235.56	229.63	do
	F.98/101/2023						231.11		

JUNIOR ENGINEER.

ASSISTANT ENGINEER

GOVERNMENT OF GOA

SD III (QC) , WRD, GOGAL, MARGAO- GOA.

NAME OF THE WORK: Improvement and Strengthening of bunds at Corjem fields from Sy.No. 108/2 to from 101/1 to Sy. 101/19 in Curtorim Constituency.

SAMPLE SENT BY: AE, SD III, WD II, WRD, Fatorda- Goa.

NAME OF THE AGENCY

TESTING PERIOD

28 days.

REPORT NO	SAMPLE NOS.	CASTING DATE	TESTING DATE	LOCATION OF SAMPLE	MIX PROPOTION	TARGET STRENGTH	Comp sth in Kg/cm2	Avg. Comp Kg/cm2	LETTER No / DATED
16.2	F.98/102/2023						231.11		No. WRD/ SD III/ WD II/
	F.98/103/2023	25-05-2024	22-06-2024		1.2.4	210 kg/cm2	217.78	228.15	F.17/ Camp /2024-25.
	F.98/104/2023						235.56		DATED: 27-05-2024
16.3	F.98/105/2023						231.11		
	F.98/106/2023	25-05-2024	22-06-2024		1.2.4	210 kg/cm2	226.67	226.67	do
	F.98/107/2023						222.22		

JUNIOR ENGINEER.

ASSISTANT ENGINEER

NO.WRD/WDXI/SDIII/TECH/W.F. 98-2023/2024-25/ 148
GOVERNMENT OF GOA

. Dated:-18/07/2024

SD III (QC) , WRD, GOGAL, MARGAO- GOA.

NAME OF THE WORK: Improvement and Strengthening of bunds at Corjem fields from Sy.No. 108/2 to from 101/1 to Sy. 101/19 in Curtorim Constituency.

SAMPLE SENT BY: AE, SD III, WD II, WRD, Fatorda- Goa.

NAME OF THE AGENCY

TESTING PERIOD

28 days.

REPORT NO	SAMPLE NOS.	CASTING DATE	TESTING DATE	LOCATION OF SAMPLE	MIX PROPOTION	TARGET STRENGTH	Comp sth in Kg/cm2	Avg. Comp Kg/cm2	LETTER No / DATED
17.1	F.98/108/2023						231.11		No. WRD/ SD III/ WD II/ F.17/ Camp /2024-25. DATED: 14-06-2024
	F.98/109/2023	27-05-2024	24-06-2024		1.2.4	210 kg/cm2	213.33	223.70	
	F.98/110/2023						226.67		
17.2	F.98/111/2023						231.11		do
	F.98/112/2023	27-05-2024	24-06-2024		1.2.4	210 kg/cm2	231.11	229.63	
	F.98/113/2023						226.67		
18.1	F.98/114/2023						226.67		do
	F.98/115/2023	28-05-2024	25-06-2024		1.2.4	210 kg/cm2	235.56	225.19	
	F.98/116/2023						213.33		
18.2	F.98/117/2023						235.56		do
	F.98/118/2023	28-05-2024	25-06-2024		1.2.4	210 kg/cm2	226.67	231.11	
	F.98/119/2023						231.11		
19.1	F.98/120/2023						231.11		do
	F.98/121/2023	31-05-2024	28-06-2024		1.2.4	210 kg/cm2	231.11	229.63	
	F.98/122/2023						226.67		
19.2	F.98/123/2023						226.67		do
	F.98/124/2023	31-05-2024	28-06-2024		1.2.4	210 kg/cm2	226.67	228.15	
	F.98/125/2023						231.11		
20.1	F.98/126/2023						226.67		do
	F.98/127/2023	1/6/2024	29-04-2024		1.2.4	210 kg/cm2	231.11	223.70	
	F.98/128/2023						213.33		
20.2	F.98/129/2023						226.67		do
	F.98/130/2023	1/6/2024	29-04-2024		1.2.4	210 kg/cm2	222.22	226.67	
	F.98/131/2023						231.11		

JUNIOR ENGINEER.

ASSISTANT ENGINEER

GOVERNMENT OF GOA SD III (QC) , WRD, GOGAL, MARGAO- GOA.

NAME OF THE WORK: Improvement and Strengthening of bunds at Corjem fields from Sy.No. 108/2 to from 101/1 to Sy. 101/19 in Curtorim Constituency.

SAMPLE SENT BY: AE, SD III, WD II, WRD, Fatorda- Goa.

NAME OF THE AGENCY

TESTING PERIOD

28 days.

REPORT NO	SAMPLE NOS.	CASTING DATE	TESTING DATE	LOCATION OF SAMPLE	MIX PROPOTION	TARGET STRENGTH	Comp sth in Kg/cm2	Avg. Comp Kg/cm2	LETTER No / DATED
21.1	F.98/132/2023						222.22		No. WRD/ SD III/ WD II/ F.17/Camp/2024-25. DATED: 14-06-2024
	F.98/133/2023	2/6/2024	30-06-2024		1.2.4	210 kg/cm2	226.67	225.19	
	F.98/134/2023						226.67		
21.2	F.98/135/2023						231.11		do
	F.98/136/2023	2/6/2024	30-06-2024		1.2.4	210 kg/cm2	226.67	228.15	
	F.98/137/2023						226.67		
21.3	F.98/138/2023						231.11		do
	F.98/139/2023	2/6/2024	30-06-2024		1.2.4	210 kg/cm2	226.67	229.63	
	F.98/140/2023						231.11		
22.1	F.98/141/2023						235.56		do
	F.98/142/2023	3/6/2024	1/7/2024		1.2.4	210 kg/cm2	217.78	228.15	
	F.98/143/2023						231.11		
22.2	F.98/144/2023						231.11		do
	F.98/145/2023	3/6/2024	1/7/2024		1.2.4	210 kg/cm2	222.22	229.63	
	F.98/146/2023						235.56		
23.1	F.98/147/2023						235.56		do
	F.98/148/2023	4/6/2024	2/7/2024		1.2.4	210 kg/cm2	213.33	226.67	
	F.98/149/2023						231.11		
23.2	F.98/150/2023						235.56		do
	F.98/151/2023	4/6/2024	2/7/2024		1.2.4	210 kg/cm2	222.22	225.19	
	F.98/152/2023						217.78		
23.3	F.98/153/2023						231.11		do
	F.98/154/2023	4/6/2024	2/7/2024		1.2.4	210 kg/cm2	226.67	229.63	
	F.98/155/2023						231.11		

JUNIOR ENGINEER.

ASSISTANT ENGINEER

**GOVERNMENT OF GOA
SD III (QC) , WRD, GOGAL, MARGAO- GOA.**

NAME OF THE WORK: Improvement and Strengthening of bunds at Corjem fields from Sy.No. 108/2 to from 101/1 to Sy. 101/19 in Curtorim Constituency.

SAMPLE SENT BY: AE, SD III, WD II, WRD, Fatorda- Goa.

NAME OF THE AGENCY				TESTING PERIOD		28 days.			
REPORT NO	SAMPLE NOS.	CASTING DATE	TESTING DATE	LOCATION OF SAMPLE	MIX PROPOTION	TARGET STRENGTH	Comp sth in Kg/cm2	Avg. Comp Kg/cm2	LETTER No / DATED
24.1	F.98/156/2023						226.67		No. WRD/ SD III/ WD II/ F.17/Camp/2024-25. DATED: 14-06-2024
	F.98/157/2023	5/6/2024	3/7/2024		1.2.4	210 kg/cm2	231.11	229.63	
	F.98/158/2023						231.11		
24.2	F.98/159/2023						226.67		do
	F.98/160/2023	5/6/2024	3/7/2024		1.2.4	210 kg/cm2	222.22	225.19	
	F.98/161/2023						226.67		
25.1	F.98/162/2023						231.11		do
	F.98/163/2023	6/6/2024	4/7/2024		1.2.4	210 kg/cm2	217.78	225.19	
	F.98/164/2023						226.67		
25.2	F.98/165/2023						222.22		do
	F.98/166/2023	6/6/2024	4/7/2024		1.2.4	210 kg/cm2	226.67	226.67	
	F.98/167/2023						231.11		
25.3	F.98/168/2023						222.22		do
	F.98/169/2023	6/6/2024	4/7/2024		1.2.4	210 kg/cm2	235.56	226.67	
	F.98/170/2023						222.22		
26.1	F.98/171/2023						231.11		do
	F.98/172/2023	7/6/2024	5/7/2024		1.2.4	210 kg/cm2	226.67	228.15	
	F.98/173/2023						226.67		
26.2	F.98/174/2023						235.56		do
	F.98/175/2023	7/6/2024	5/7/2024		1.2.4	210 kg/cm2	231.11	229.63	
	F.98/176/2023						222.22		
26.3	F.98/177/2023						231.11		do
	F.98/178/2023	7/6/2024	5/7/2024		1.2.4	210 kg/cm2	222.22	226.67	
	F.98/179/2023						226.67		

JUNIOR ENGINEER.

ASSISTANT ENGINEER

**GOVERNMENT OF GOA
SD III (QC) , WRD, GOGAL, MARGAO- GOA.**

NAME OF THE WORK: Improvement and Strengthening of bunds at Corjem fields from Sy.No. 108/2 to from 101/1 to Sy. 101/19 in Curtorim Constituency.

SAMPLE SENT BY: AE, SD III, WD II, WRD, Fatorda- Goa.

NAME OF THE AGENCY				TESTING PERIOD		28 days.			
REPORT NO	SAMPLE NOS.	CASTING DATE	TESTING DATE	LOCATION OF SAMPLE	MIX PROPOTION	TARGET STRENGTH	Comp sth in Kg/cm2	Avg. Comp Kg/cm2	LETTER No / DATED
27.1	F.98/180/2023						226.67		No. WRD/ SD III/ WD II/ F.17/ Camp /2024-25. DATED: 14-06-2024
	F.98/181/2023	8/6/2024	6/7/2024		1.2.4	210 kg/cm2	231.11	226.67	
	F.98/182/2023						222.22		
27.2	F.98/183/2023						222.22		
	F.98/184/2023	8/6/2024	6/7/2024		1.2.4	210 kg/cm2	235.56	229.63	do
	F.98/185/2023						231.11		
27.3	F.98/186/2023						226.67		
	F.98/187/2023	8/6/2024	6/7/2024		1.2.4	210 kg/cm2	231.11	229.63	do
	F.98/188/2023						231.11		
28.1	F.98/189/2023						222.22		
	F.98/190/2023	9/6/2024	7/7/2024		1.2.4	210 kg/cm2	226.67	228.15	do
	F.98/191/2023						235.56		
28.2	F.98/192/2023						226.67		
	F.98/193/2023	9/6/2024	7/7/2024		1.2.4	210 kg/cm2	231.11	226.67	do
	F.98/194/2023						222.22		
28.3	F.98/195/2023						231.11		
	F.98/196/2023	9/6/2024	7/7/2024		1.2.4	210 kg/cm2	235.56	226.67	do
	F.98/197/2023						213.33		

JUNIOR ENGINEER.

ASSISTANT ENGINEER

**GOVERNMENT OF GOA
SD III (QC) , WRD, GOGAL, MARGAO- GOA.**

NAME OF THE WORK: Improvement and Strengthening of bunds at Corjem fields from Sy.No. 108/2 to from 101/1 to Sy. 101/19 in Curtorim Constituency.

SAMPLE SENT BY: AE, SD III, WD II, WRD, Fatorda- Goa.

NAME OF THE AGENCY				TESTING PERIOD		28 days.			
REPORT NO	SAMPLE NOS.	CASTING DATE	TESTING DATE	LOCATION OF SAMPLE	MIX PROPOTION	TARGET STRENGTH	Comp sth in Kg/cm2	Avg. Comp Kg/cm2	LETTER No / DATED
29.1	F.98/198/2023						231.11		No. WRD/ SD III/ WD II/
	F.98/199/2023	10/6/2024	8/7/2024		1.2.4	210 kg/cm2	222.22	228.15	F.17/ Camp /2024-25.
	F.98/200/2023						231.11		DATED: 14-06-2024
29.2	F.98/201/2023						235.56		
	F.98/202/2023	10/6/2024	8/7/2024		1.2.4	210 kg/cm2	222.22	225.19	do
	F.98/203/2023						217.78		
29.3	F.98/204/2023						235.56		
	F.98/205/2023	10/6/2024	8/7/2024		1.2.4	210 kg/cm2	226.67	228.15	do
	F.98/206/2023						222.22		
30.1	F.98/207/2023						231.11		
	F.98/208/2023	11/6/2024	9/7/2024		1.2.4	210 kg/cm2	226.67	226.67	do
	F.98/209/2023						222.22		
30.2	F.98/210/2023						231.11		
	F.98/211/2023	11/6/2024	9/7/2024		1.2.4	210 kg/cm2	222.22	225.18	do
	F.98/212/2023						222.22		
30.3	F.98/213/2023						235.56		
	F.98/214/2023	11/6/2024	9/7/2024		1.2.4	210 kg/cm2	217.78	226.67	do
	F.98/215/2023						226.67		

JUNIOR ENGINEER.

ASSISTANT ENGINEER

**GOVERNMENT OF GOA
SD III (QC) , WRD, GOGAL, MARGAO- GOA.**

NAME OF THE WORK: Improvement and Strengthening of bunds at Corjem fields from Sy.No. 108/2 to from 101/1 to Sy. 101/19 in Curtorim Constituency.

SAMPLE SENT BY: AE, SD III, WD II, WRD, Fatorda- Goa.

NAME OF THE AGENCY				TESTING PERIOD		28 days.			
REPORT NO	SAMPLE NOS.	CASTING DATE	TESTING DATE	LOCATION OF SAMPLE	MIX PROPOTION	TARGET STRENGTH	Comp sth in Kg/cm2	Avg. Comp Kg/cm2	LETTER No / DATED
30.1	F.98/216/2023						226.67		No. WRD/ SD III/ WD II/
	F.98/217/2023	12/6/2024	10/7/2024		1.2.4	210 kg/cm2	231.11	229.63	F.17/ Camp /2024-25.
	F.98/218/2023						231.11		DATED: 14-06-2024
30.2	F.98/219/2023						226.67		
	F.98/220/2023	12/6/2024	10/7/2024		1.2.4	210 kg/cm2	222.22	225.19	do
	F.98/221/2023						226.67		
30.3	F.98/222/2023						231.11		
	F.98/223/2023	12/6/2024	10/7/2024		1.2.4	210 kg/cm2	217.78	225.19	do
	F.98/224/2023						226.67		
31.1	F.98/225/2023						222.22		
	F.98/226/2023	13-06-2024	11/7/2024		1.2.4	210 kg/cm2	226.67	226.67	do
	F.98/227/2023						231.11		
31.2	F.98/228/2023						222.22		
	F.98/229/2023	13-06-2024	11/7/2024		1.2.4	210 kg/cm2	235.56	226.67	do
	F.98/230/2023						222.22		
31.3	F.98/231/2023						231.11		
	F.98/232/2023	13-06-2024	11/7/2024		1.2.4	210 kg/cm2	208.89	222.22	do
	F.98/233/2023						226.67		

JUNIOR ENGINEER.

ASSISTANT ENGINEER