

NO.WRD/WDXI/SDIII/TECH/W.F. 162/2024/2025-26/162 . Dated:-10/06/2025
GOVERNMENT OF GOA
SD III (QC) , WRD, GOGAL, MARGAO- GOA.

NAME OF THE WORK: Improvement to existing Bhindezor (Spring) at Bhindem- Betoda in V.P. Betoda, Nirankal Conxem Codar of Shiroda Constituency.

SAMPLE SENT BY: AE, SD IV, WD XI, WRD, Ponda- Goa.

NAME OF THE AGENCY				TESTING PERIOD		28 days.			
REPORT NO	SAMPLE NOS.	CASTING DATE	TESTING DATE	LOCATION OF SAMPLE	MIX PROPOTION	TARGET STRENGTH	Comp sth in Kg/cm2	Avg. Comp Kg/cm2	LETTER No / DATED
1.1	F. 162/11/2024						222.22		No. WRD/WD XI/ SD IV/
	F. 162/12/2024	4/5/2025	2/6/2025	for cut off U/s & D/s Central cut off	1.2.4	210 kg/cm2	226.67	226.67	F. CF/142/2025-26.
	F. 162/13/2024						231.11		DATED: 19-05-2025.
1.2	F. 162/14/2024						235.56		
	F. 162/15/2024	4/5/2025	2/6/2025	for cut off U/s & D/s Central cut off	1.2.4	210 kg/cm2	226.67	231.11	do
	F. 162/16/2024						231.11		
2.1	F. 162/17/2024						240.00		
	F. 162/18/2024	5/5/2025	2/6/2025	Apron U/s & D/s	1.2.4	210 kg/cm2	222.22	229.63	do
	F. 162/19/2024						226.67		
2.2	F. 162/20/2024						231.11		
	F. 162/21/2024	5/5/2025	2/6/2025	Apron U/s & D/s	1.2.4	210 kg/cm2	235.56	232.59	do
	F. 162/22/2024						231.11		
3.1	F. 162/23/2024						231.11		
	F. 162/24/2024	8/5/2025	5/6/2025	Retaining wall foundation	1.2.4	210 kg/cm2	226.67	231.11	do
	F. 162/25/2024						235.56		
3.2	F. 162/26/2024						226.67		
	F. 162/27/2024	8/5/2025	5/6/2025	Retaining wall foundation	1.2.4	210 kg/cm2	240.00	232.59	do
	F. 162/28/2024						231.11		
4.1	F. 162/29/2024						226.67		
	F. 162/30/2024	9/5/2025	6/6/2025	Retaining wall , Abutment	1.2.4	210 kg/cm2	231.11	226.67	do
	F. 162/31/2024			Foundation			222.22		
4.2	F. 162/32/2024						235.56		
	F. 162/33/2024	9/5/2025	6/6/2025	Retaining wall , Abutment	1.2.4	210 kg/cm2	231.11	228.15	do
	F. 162/34/2024			Foundation			217.78		

JUNIOR ENGINEER.

ASSISTANT ENGINEER

GOVERNMENT OF GOA
SD III (QC) , WRD, GOGAL, MARGAO- GOA.

NAME OF THE WORK: Improvement to existing Bhindezor (Spring) at Bhindem- Betoda in V.P. Betoda, Nirankal Conxem Codar of Shiroda Constituency.

SAMPLE SENT BY: AE, SD IV, WD XI, WRD, Ponda- Goa.

NAME OF THE AGENCY				TESTING PERIOD		28 days.			
REPORT NO	SAMPLE NOS.	CASTING DATE	TESTING DATE	LOCATION OF SAMPLE	MIX PROPOTION	TARGET STRENGTH	Comp sth in Kg/cm2	Avg. Comp Kg/cm2	LETTER No / DATED
4.3	F. 162/35/2024						240.00		No. WRD/WD XI/ SD IV/
	F. 162/36/2024	9/5/2025	6/6/2025	Retaining wall , Abutment	1.2.4	210 kg/cm2	231.11	229.63	F. CF/ 142 /2025-26.
	F. 162/37/2024			Foundation			217.78		DATED: 19-05-2025.
4.4	F. 162/38/2024						226.67		
	F. 162/39/2024	9/5/2025	6/6/2025	Retaining wall , Abutment	1.2.4	210 kg/cm2	226.67	225.19	do
	F. 162/40/2024			Foundation			222.22		
5.1	F. 162/41/2024						244.44		
	F. 162/42/2024	11/5/2025	9/6/2025	1st Lift Retaining wall	1.2.4	210 kg/cm2	222.22	232.59	do
	F. 162/43/2024						231.11		
5.2	F. 162/44/2024						231.11		
	F. 162/45/2024	11/5/2025	9/6/2025	1st Lift Retaining wall	1.2.4	210 kg/cm2	231.11	229.63	do
	F. 162/46/2024						226.67		
5.3	F. 162/47/2024						235.56		
	F. 162/48/2024	11/5/2025	9/6/2025	1st Lift Retaining wall	1.2.4	210 kg/cm2	222.22	228.15	do
	F. 162/49/2024						226.67		
5.4	F. 162/50/2024						235.56		
	F. 162/51/2024	11/5/2025	9/6/2025	1st Lift Retaining wall	1.2.4	210 kg/cm2	231.11	231.11	do
	F. 162/52/2024						226.67		
6.1	F. 162/53/2024						226.67		
	F. 162/54/2024	12/5/2025	9/6/2025	1st Lift Retaining wall	1.2.4	210 kg/cm2	235.56	225.19	do
	F. 162/55/2024			& Abutment			213.33		
6.2	F. 162/56/2024						235.56		
	F. 162/57/2024	12/5/2025	9/6/2025	1st Lift Retaining wall	1.2.4	210 kg/cm2	222.22	228.15	do
	F. 162/58/2024			& Abutment			226.67		

JUNIOR ENGINEER.

ASSISTANT ENGINEER

GOVERNMENT OF GOA

SD III (QC) , WRD, GOGAL, MARGAO- GOA.

NAME OF THE WORK: Improvement to existing Bhindezor (Spring) at Bhindem- Betoda in V.P. Betoda, Nirankal Conxem Codar of Shiroda Constituency.

SAMPLE SENT BY: AE, SD IV, WD XI, WRD, Ponda- Goa.

NAME OF THE AGENCY					TESTING PERIOD		28 days.		
REPORT NO	SAMPLE NOS.	CASTING DATE	TESTING DATE	LOCATION OF SAMPLE	MIX PROPOTION	TARGET STRENGTH	Comp sth in Kg/cm2	Avg. Comp Kg/cm2	LETTER No / DATED
7.1	F. 162/59/2024						231.11		No. WRD/WD XI/ SD IV/
	F. 162/60/2024	13-05-2025	10/6/2025	2nd Lift Retaining wall &	1.2.4	210 kg/cm2	231.11	229.63	F. CF/142/2025-26.
	F. 162/61/2024			Abutment			226.67		DATED: 19-05-2025.
7.2	F. 162/62/2024						235.56		
	F. 162/63/2024	13-05-2025	10/6/2025	2nd Lift Retaining wall &	1.2.4	210 kg/cm2	222.22	228.15	do
	F. 162/64/2024			Abutment			226.67		

JUNIOR ENGINEER.

ASSISTANT ENGINEER