

GOVERNMENT OF GOA
SD III (QC) , WRD, GOGAL, MARGAO- GOA.

NAME OF THE WORK: Providing and laying parallel 500 mm dia Ductile Iron pipeline for gravity main from Tank No. 1 to Tank No.2
at L. I. Scheme Naikaband , Vaddem Reh. Site.

SAMPLE SENT BY: A.E, SD IV, WD X, Pajimol-Sanguem- Goa.

NAME OF THE AGENCY

TESTING PERIOD

28 days.

REPORT NO	SAMPLE NOS.	CASTING DATE	TESTING DATE	LOCATION OF SAMPLE	MIX PROPOTION	REQUIRED STRENGTH	Comp sth in Kg/cm2	Avg. Comp Kg/cm2	LETTER No / DATED
	43			Tank I			275.55		
1	44	9/10/2019	6/11/2019	Bed & outside ring	1.1.5.3	265 kg/cm2	271.11	272.59	NO: WRD/WDX/SD IV/ F.E.60/138/2019-20
	45						271.11		DATED 25/10/2019
	46			Tank II			280.00		
2	47	10/10/2019	7/11/2019	Bed & outside ring		265 kg/cm2	271.11	274.07	do
	48						271.11		
	49			Tank I			271.11		
3	50	15-10-2019	12/11/2019	Vertical internal		265 kg/cm2	266.66	268.14	do
	51						266.66		
	52			Tank II			266.66		
4	53	16-10-2019	13/11/1900	Vertical internal		265 kg/cm2	262.22	266.66	do
	54						271.11		
	55			Tank I &II			266.66		
5	56	18-10-2019	15-11-2019	outside ring		265 kg/cm2	271.11	269.63	do
	57						271.11		

Joaquim Antao
JUNIOR ENGINEER.

Pravin C Parsekar
ASSISTANT ENGINEER

GOVERNMENT OF GOA
SD III (QC) , WRD, GOGAL, MARGAO- GOA.

NAME OF THE WORK: Providing and laying parallel 500 mm dia Ductile Iron pipeline for gravity main from tank No. 1 at L. I. Scheme Naikaband , Vaddem Reh. Site.

SAMPLE SENT BY: A.E, SD IV, WD X, Pajimol-Sanguem- Goa.

NAME OF THE AGENCY

TESTING PERIOD

28 days.

REPORT NO	SAMPLE NOS.	CASTING DATE	TESTING DATE	LOCATION OF SAMPLE	MIX PROPOTION	REQUIRED STRENGTH	Comp sth in Kg/cm2	Avg. Comp Kg/cm2	LETTER No / DATED
1									
2									

JUNIOR ENGINEER.

ASSISTANT ENGINEER