

GOVERNMENT OF GOA
WATER RESOURCES DEPARTMENT
S.D.III., Works Div. XI, QUALITY CONTROL LABORATORY
Gogol - Margao - Goa.

No. WRD / WD XI / SDIII / F.59. W.F. 05/2020 / 175 / 2020-21

dated: 08/12/2020

Name of the Work: Construction of Protection Wall for hillock adjoining Chalta No. 220 of P.T. sheet No. 3 at Aquem of Margao- Goa.

Sample Sent by :- Assistant Engineer, SD III, WD III, WRD, Gogol- Margao- Goa.

Letter no:- No. WRD/ SD III/WD III/ F.259/2020-21/273.

Dated:- 21-11-2020

Received On: 21-11-2020

Date of Tesing: 30-11-2020

REPORT

Sr. No.	Type of Sample	Tested for	Result	Permissible value	REMARKS
18/20	Coarse Sand	FM Silt & Clay Grading	2.608 1.40% Zone II	2.3 to 3.1 Upto 5% I to III Zone	
19/20	Aggregate-20 mm	Grading		As per IS-383-1970 (Re-affirmed in 1990)	To get the 20mm graded aggregate nominal size blend
20/20	Aggregate- 10 mm	Grading		As per IS-383-1970 (Re-affirmed in 1990)	20mm & 10 mm metal in 1:1 proportion.

Junior Engineer

Assistant Engineer

Copy submitted to

- 1) Assistant Engineer, SDIII, WD III, WRD, Gogol- Margao, Goa.
- 2) The Executive Engineer, Works Division III, WRD, Ponda, Goa.
- 3) Executive Engineer, WD XI, WRD, Rawanfond -Goa.
- 4) Office File.