GOVERNMENT OF GOA QUALITY CONTROL LABORATORY WATER RESOURCES DFEPARTMENT

 $\underline{\textbf{Test Report No.: WRD/Q.C./ F.6-4/Aggr-T-159,160/Lab/71/2022-23} \quad \underline{\textbf{Dated: 16/05/2022.}} \quad \underline{\textbf{Laboratory: Bicholim-Goa.}}$

Sand –T:-5284. <u>Sub Div</u>: V(QC)/W.D.VIII/Bicholim Goa.

Sub: Construction of Kamurlim Tail Minor and its Network Kamurlim Branch of LBMC of TIP at Village Kamurlim in Bardez Taluka.

Ref to requisition No:-SDI/WDVIII/WRD/WF.29/2022-23/19 Dated: 06/05/2022.

Qty. Received: 1 bags each Date of Receipt: 09/05/2022 Tested on:- 11 & 12/05/2022 Ref to Specification: CPWD 2009, Vol. I&IS:4031-4-1968

Sample: Sand, 20mm, **O.S. No.** 0727, 0728 & 0729/R.K. **Lab. Sample No.**: 4359 to 4361 **Tested by**: Mrs. R. R. Kadam A.E.

12.5mm size aggrt..

REPORT 01 OF 01

Sr. No.	Description of sample	Tested for	Results	Max. /Min. value permissible	Remark
1. 2.	20 mm Size Aggregate: 12.5 mm Size Aggregate:	Particle size distribution: Particle size distribution:	It is single sized aggregate of It is not single sized aggrega	of 20 mm nominal size. (Qty. rep te of 12.5 mm nominal size. (Qty. rep	m ³) m ³)
	REMARK: After blending 20 mm aggregate with 12.5 mm aggregates at the ratio of $\underline{1:2}$ by weight; it is satisfying therequired criteria for graded aggregate of 20 mm nominal size.				
3.	Coarse Sand: (L.S.No.4361)	iii) Fineness Modulus iv) Grading Zone	: - 5.68% : - 3.65% : - I	issible limits of the Coarse sand.	

Copy to: 1. The Assistant Engineer, SDI, WDVIII, WRD, Karaswada, Bardez - Goa.

- 2. Copy Submitted to The Superintending Engineer, CPO, WRD, Sinchai Bhavan Porvorim-Goa for kind Information
- 3. Copy Submitted to The Executive Engineer, WDVIII, WRD, Karaswada, Bardez Goa
- 4. Q.C. Lab file 5. Bill File.

Assistant Engineer