

**GOVERNMENT OF GOA
QUALITY CONTROL LABORATORY
WATER RESOURCES DEPARTMENT**

Test Report No.: WRD/Q.C./F.6-4/Aggr-T- 151,152/Lab/53/2022-23 **Dated:-** 28/ 04 /2022.

Laboratory: Bicholim

Sand –T:-5283. Cement-T:- 1364.

Sub Div: V(QC)/WRD/Bicholim Goa.

Sub:- Construction of Irrigation well in the field of Shri Sanjay Sadanand Tendulkar in Sy No. ¾ in Village Codiem V.P. Pissurlem in Sattari Taluka.

Ref to requisition No:- MIN/WDVI/WRD/SDII/f.62/21-22/496 **Dated :-** 31/03/2022

Qty. Received: 1 bags each **Date of Receipt:-** 21/04/2022 **Tested on:-** 23,25 & 26 /04/2022 **Ref to Specification:** CPWD 2009, Vol. I&IS:4031-4-1968

Sample:Sand,20mm, **O.S. No.**8325,8326,8379 & 8307/SS **Lab. Sample No.:** 3970 to 3973 **Tested by:-** Mrs. S. B. Naik Shirodkar J.E.

12.5mm size aggrt., Cement

R E P O R T 01 OF 01

Sr. No.	Description of sample	Tested for	Results	Max. /Min. value permissible	Remark
1.	20 mm Size Aggregate:	Particle size distribution:	It is single sized aggregate of 20 mm nominal size.	(Qty. rep. – --m ³)	
2.	12.5 mm Size Aggregate:	Particle size distribution:	It is not single sized aggregate of 12.5 mm nominal size.	(Qty. rep. – -- m ³)	
REMARK:- After blending 20 mm aggregate with 12.5 mm aggregates at the ratio of 1:2 by weight; it is satisfying therequired criteria for graded aggregate of 20 mm nominal size.					
3.	Coarse Sand: (L.S.No.3972)	i) Silt & Clay by S.A. method ii) Silt by sedimentation iii) Fineness Modulus iv) Grading Zone	: - 4.80% : - 5.55% : - 2.57% : - II		
REMARK:- The observed results are within the permissible limits of the coarse sand.					
4.	Cement: J.K. Cement, bearing IS:269 Ordinary Portland cement, Manuf. date: W- 14, M- 04, Year-2022 CM/L =0003401033 Qty. rep. – ____ --.	i) Fineness of Cement ii) Consistency of cement iii) Initial Setting Time iv) Final Setting Time	: 1.12% : 32.00% : 165 minutes : 285 minutes	----- (It should not be more than 10%) (It should be in the neighborhood of 35%) ---- (It should not be less than 30 minutes) -- (It should not be more than 600 minutes)	
To be used for Concrete Mix 1:1.5:3 -REMARK: The observed results are within the permissible limit for Ordinary Portland cement.					

Copy to: 1. The Assistant Engineer, SDII,WDVI,WRD, Valpoi – Sattari – Goa.

2. Copy Submitted to The Superintending Engineer, CPO, WRD, Sanchai Bhavan, Porvorim – Goa for kind information.

3. Copy Submitted to The Executive Engineer, WDVI, WRD, Bicholim – Goa

4. Q.C. Lab file 5. Bill file.

Junior Engineer

Assistant Engineer