GOVERNMENT OF GOA QUALITY CONTROL LABORATORY WATER RESOURCES DFEPARTMENT

<u>Test Report No.: WRD/Q.C./F.6-4/Aggr-T-115,116/Lab/342/2021-22</u> Dated: 26/03/2022. <u>I</u>

22. <u>Laboratory</u>: Bicholim

Sand –T: 5262 Cement-T: 1345

Sub Div: V (QC)/WRD/Bicholim Goa.

Sub:- Construction of Irrigation well in the field bearing Survey No.51/1, at Saleli Village Panchayat at Honda in Sattari Taluka. Ref to requisition No:- F.50/SDIV/WDVI/WRD/2021-22/248 Dated :- 21/03/2022 Otra Preside 1 have each Date of President 21/02/2022 Tested are 22.24 & 25/02/2022 Pafete Specifications CDWD

 Qty. Received:
 1 bags each
 Date of Receipt:
 21/03/2022
 Tested on:
 23,24 & 25/03/2022
 Ref to Specification:
 CPWD 2009, Vol. I&IS:4031-4-1968

 Sample:
 Sand,20mm,
 O.S. N: 269,270,268 & 242/R.K.
 Lab. Sample No.:
 3426 To 3429
 Tested by:
 Mrs. R.R.Kadam A.E.

 12.5mm size aggrt., Cement
 Cement
 Cement
 Cement
 CPWD 2009, Vol. I&IS:4031-4-1968

R E P O RT 01 OF 01

Sr. No.	Description of sample	Tested for	Results	Max. /Min. value permissible	Remarks
1.	20 mm Size Aggregate:	Particle size distribution:	It is single sized ag	gregate of 20 mm nominal size. (Qty. rep. –	m ³)
2.	<u>12.5 mm Size Aggregate</u> :	Particle size distribution:	It is not single sized	d aggregate of 12.5 mm nominal size. (Qty. rep	m ³)
	<u>REMARK</u> : After blending 20 mm aggregate with 12.5 mm aggregates at the ratio of <u>1:1</u> by weight; it is satisfying the required criteria for graded aggregate of 20 mm nominal size.				
3.	Coarse Sand:	i) Silt & Clay by S.A.	method : - 5.80%		
	(L.S.No.3428)	ii) Silt by sedimentatio	n :- 5.55%		
		iii) Fineness Modulus	: - 2.37%		
		iv) Grading Zone	:- III		
	To be used for <u>REMARK</u>: The observed results are within the permissible limits of the coarse sand.				
4.	Cement:	i) Fin	eness of Cement	: 99.09% (It should not be mo	re than 10%)
	Ordinary Portland cement, iii		nsistency of cement	: 30.00% (It should be in the neighborhood	l of 35%)
			tial Setting Time	: 160 minutes (It should not be less that	in 30 minutes)
			nal Setting Time	: 285 minutes (It should not be more that	,
	CM/L = 0003401033	-,,	6		
	Qty. rep. –.				
	To be used for REMARK: The observed results are within the permissible limit for Ordinary Portland cement.				

Copy to: 1. The Assistant Engineer, SDIV, WDVI, WRD, Bicholim – Goa.

2. Copy Submitted to The Superintending Engineer, CPO, WRD, Porvorim – Goa for kind information.

3. Copy Submitted to The Executive Engineer, W.D.VI, WRD, Bicholim – Goa

4. Q.C. Lab file 5. Bill File.